

Features & Benefits

- Thermal resistance 100μm, 0.06 °C-in²/W
- Product Thermal conductivity of 12 W/m-K
 - (2oz Cu x 100μm SFL-12 x 1.5 Al)
- High Electrical Strength
- Lead-free solder compatible
- RoHS compliant and environmentally green
- **Available as a laminated panel, RCC or prepreg**
- **Available on aluminum and copper base substrates**
 - Other substrates materials may be available.

TCLAD Metal Core PCB's (MCPCB's) minimize thermal impedance and conduct heat more efficiently than standard printed wiring boards (PWB's).

The distinguishing difference of Thermal Clad resides in the dielectric. This datasheet highlights the performance characteristics of TCLAD SFL-12 dielectric.

Applications

- High power density applications where achieving low thermal resistance is required, such as:
- LED Lighting
- Power conversion
- Motor drives
- Solid state relays

Configurations

Base Metal	Thickness mm (mil)
• 5052 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 6061 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 1050 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 4045 Aluminum	1.5 (59), 2.0 (80)
• Copper C1100	1.0 (40)*, 1.5 (59)*, 2.0 (80)
Copper Foil	Weight oz (thickness μm)
• ED Copper	1oz (35), 2oz (70), 3oz (105), 4oz (140), 6oz (210)
• RA	8oz (280), 10oz (350)

* Most common thicknesses

** Other thicknesses and alloys may be available.

Please contact TCLAD sales department for more information.

We provide custom solutions for your applications. For Further inquiries, please contact your local sales agent or directly to TCLAD sales in your region.

Item	Thickness	Unit	Value (Typ.)	Method
Thermal Properties				
Product Thermal Conductivity		W/m-K	12	TO220
Dielectric Thermal Conductivity		W/m-K	3.2	ASTM D5470
Thermal Resistance	100μm (4mil)	°C-in ² /W	0.06	ASTM D5470
Thermal Impedance	100μm (4mil)	°C/W	0.08	TO-220
Electrical Properties				
Dielectric Constant		-	4.2	IPC-TM-650 2.5.5.3
Dissipation Factor	100μm (4mil)	1MHz	0.011	IPC-TM-650 2.5.5.3
Capacitance	100μm (4mil)	pF	38	IPC-TM-650 2.5.5.3
Volume Resistivity		Ω-cm	10 ¹³	IPC-TM-650 2.5.17.1
Surface Resistivity		Ω/sq	10 ¹³	IPC-TM-650 2.5.17.1
Breakdown Voltage	80μm (3.2mil) 100μm (4mil) 150μm (6mil)	KVAC	4 5 7	ASTM D149
Mechanical Properties				
Color		-	Off-white	Visual
Peel Strength @ 25°C		Kg/cm	>1.3	IPC TM-650 2.4.8
Glass Transition (Tg)		°C	180	IPC TM-650 2.4.25
CTE in X,Y/Z Axis <Tg		μm/m°C	15	IPC TM-650 2.4.24.5
CTE in X,Y/Z Axis >Tg		μm/m°C	18	IPC TM-650 2.4.24.5
Storage Modulus @ 25°C		GPa	18	ASTM D638
Storage Modulus		GPa	18 (25 °C) 10.8 (150 °C)	ASTM D4065
Decomposition Temperature (2% loss)		°C	370	IPC TM-650 2.4.24.6
Decomposition Temperature (5% loss)		°C	400	IPC TM-650 2.4.24.6
Chemical Properties				
Water Vapor Retention		%	< 0.5	ASTM E595
Out-Gassing Total Mass Loss		%	< 0.1	ASTM E595
Collect Volatile Condensable Material		%	< 0.1	ASTM E595
Agency Ratings & Durability (UL: E121882)				
UL Maximum Operating Temperature (MOT)		°C	130	UL 746
UL Flammability		-	V-0	UL 94
UL Comparative Tracking Index		(CTI)	600	UL 746E

