

Features & Benefits

- Very low thermal resistance 100μm, 0.015 °C-in²/W
- Product Thermal conductivity of 15 W/m-K
 - Based on (2oz Cu x 100μm SPL-15 HT x 1.5 Al)
- Dielectric Thermal Conductivity 10 W/m-K
- High operating temperature, ~ 200°C
- Lead-free solder compatible
- RoHS compliant and environmentally green
- **Available as a laminated panel, RCC or prepreg**
- **Available on aluminum and copper base substrates**
- Other substrates materials may be available.
- TCLAD Metal Core PCB's (MCPCB's) minimize thermal impedance and conducts heat more efficiently than standard printed wiring boards (PWB's).
- The differentiating technology of Thermal Clad resides in the dielectric. This datasheet highlights the performance characteristics of TCLAD SPL-15.

Applications

- High power density applications which required low thermal resistance
- Power conversion, Inverter, DC/DC, AC/DC
- Industrial motor drives
- High temperature SiC IGBT modules

Configurations

Base Metal	Thickness mm (mil)
• 5052 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 6061 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 1050 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 4045 Aluminum	1.5 (59), 2.0 (80)
• Copper C1100	1.0 (40)*, 1.5 (59)*, 2.0 (80)
Copper Foil	Weight oz (thickness μm)
• ED Copper:	1oz (35), 2oz (70), 3oz (105), 4oz (140), 6oz (210)
• RA Copper:	8oz (280), 10oz (350), higher

* Most common thicknesses

** Other thicknesses and alloys may be available.

Please contact TCLAD sales department for more information.

We provide custom solutions for your applications. For Further inquiries, please contact your local sales agent or directly to TCLAD sales in your region.

TCLAD

US Sales: us@tclad.com
 APAC Sales: apac@tclad.com
 Europe Sales: eu@tclad.com
www.tclad.com



All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKET ABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before use, user shall determine the suitability of the product for its intended use, and the user assumes all risk and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE DIRECT, INCIDENTAL OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE THE PRODUCT. No statement, purchase order or recommendation by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer. All marks used above are trademarks and/or registered trademarks of TCLAD Inc and its affiliates in the U.S., Germany and elsewhere. © 2021 TCLAD Inc. All rights reserved. US



Rev 2024 D24-009

Item	Thickness	Unit	Value (Typ.)	Method
Thermal Properties				
Product Thermal Conductivity		W/m-K	15	TO-220 Method
Dielectric Thermal Conductivity		W/m-K	10	ASTM D5470
Thermal Resistance	100μm (4mil)	°C-cm ² /W (°C-in ² /W)	0.096 (0.015)	ASTM D5470
Electrical Properties				
Dielectric Constant		-	4.5	IPC-TM-650 2.5.5.3
Dissipation Factor	100μm (4mil)	1MHz	0.007	IPC-TM-650 2.5.5.3
Capacitance	100μm (4mil)	pF	41	IPC-TM-650 2.5.5.3
Volume Resistivity		Ω-cm	10 ¹³	IPC-TM-650 2.5.17.1
Surface Resistivity		Ω/sq	10 ¹³	IPC-TM-650 2.5.17.1
Breakdown Voltage	80μm (3.2mil) 100μm (4mil) 150μm (6mil)	KVAC	3 4 6	ASTM D149
Mechanical Properties				
Color		-	Light brown	Visual
Peel Strength @ 25°C		Kg/cm (lb/in)	1.0 (5.6)	IPC-TM-650 2.4.8
Glass Transition (Tg)		°C	270	IPC-TM-650 2.4.25
CTE in X,Y/Z Axis <Tg		μm/m°C	11.7	IPC-TM-650 2.4.24.5
CTE in X,Y/Z Axis >Tg		μm/m°C	24.3	IPC-TM-650 2.4.24.5
Youngs Modulus		GPa	30	ASTM D638
Storage Modulus		GPa	30 (25 °C) 22.6 (150 °C)	ASTM D4065
Solder Heat Resistance (min)		°C	>60	IPC-TM-650 2.4.24.1
Decomposition Temperature (2% loss)		°C	390	IPC-TM-650 2.4.24.6
Decomposition Temperature (5% loss)		°C	460	IPC-TM-650 2.4.24.6
Chemical Properties				
Water Vapor Retention		%	< 0.5	ASTM E595
Out-Gassing Total Mass Loss		%	< 0.1	ASTM E595
Collect Volatile Condensable Material		%	< 0.1	ASTM E595
Agency Ratings & Durability- (UL: I21882)				
UL Maximum Operating Temperature (MOT)		°C	155	UL 746
UL Flammability		-	V-0	UL 94
UL Comparative Tracking Index (CTI)			<600	UL 746E